

# Anti-Vandalism Films: Data Sheet Saint-Gobain Graffitigard<sup>™</sup> 4PLUS

# **Physical Characteristics**

| PERFORMANCE                       | VALUE                | METHOD      | Adhesion<br>Adhesion is measured by peeling |
|-----------------------------------|----------------------|-------------|---|
| Number of layers                  | 4                    | NA          | specimens at a 180° angle from the          |
| Thickness                         |                      | ASTM D 3652 | underlying substrate. Peel adhesion         |
| Overall                           | 17.4 mil (.017 in)   |             | is the average result for the strips        |
| Single layer                      | 4.3 mil (.004 in)    |             | tested in Newtons per meter.                |
| Peel adhesion                     |                      | ASTM D 3330 | Specimens are applied to substrate          |
| Adhesion to glass                 | 5.6 oz/in. (61 N/m)  |             | using standard application practices        |
| Adhesion between layers           | 1.5 oz/in. (16 N/m)  |             | Adhesion to glass and between               |
| Residual adhesive                 | None                 |             | layers is measured.                         |
| Haze / Luminous Transmittance (*) |                      | ASTM D 1003 | Scratch Resistance                          |
| Visible light                     | 92%                  |             | Scratch resistance is measured              |
| Haze                              | 2.5%                 |             | testing using the Taber Haze                |
| Clarity                           | 98%                  |             | Abraser. Specimens are subjected            |
| Abrasion resistance               | -1.1 mg / 100 cycles | ASTM D 4060 | to 100 cycles with a 1,000 gm weigh         |
|                                   | 5,11                 |             | Results are expressed by changes in         |
| (*) without liner                 |                      |             | weight loss in mg/# of cycles.              |

. .. .

#### **Ordering Information for Graffitigard 4PLUS**

| Delivery format       | Rolls                         | Tailor-made cut-to-size shapes             |
|-----------------------|-------------------------------|--|
| Roll Width and Length | 60 in x 50 to 300 linear feet | (Includes tabbing to peel away each layer) |
|                       |                               | 20 cut-to-size shapes per box              |

#### Storage

Graffitigard 4PLUS should be stored in a dry, controlled environment. The temperature should not exceed 95° F nor go below 50° F. The film should always be stored in the original packaging with the end plugs securely placed on the core.

### Disclaimer

These test data contain results arrived at after employing specific test procedures and standards. The included data do not constitute a recommendation for, endorsement of, or certification of the product or material tested. These data are provided for informational purposes only and are not to be considered part of merchantability or fitness for a particular purpose, that its products will conform to these test data. Extrapolation of data from the sample or samples relation to the batch or lot from which data were obtained may not correlate and should be interpreted accordingly with caution. Saint-Gobain shall not be responsible for variations in quality, composition, appearance, performance, or other feature of similar subject matter produced by persons or under conditions over which Solar Gard has no control.

## www.custom-films.com

Saint-Gobain High Performance Solutions 4540 Viewridge Avenue San Diego, CA 92123 Tel: 877.273.4364 E-mail: info@solargard.com

SK0253SGG4PLUSDS 7/19 © Copyright 2019, Saint-Gobain High Performance Solutions and/or its affiliates All Rights Reserved • www.solargard.com

Please recycle